AMENDMENTS TO THE CLAIMS:

Kindly cancel claims 1, 2, 4, 5 and 7-10, without prejudice, and add new claims 11-23,

as shown below.

This listing of claims will replace all prior versions and listings of claims in the

Application:

Claims 1 - 10 (cancelled)

Claim 11 (new): A liquid fuel composition for an internal combustion engine having fuel

delivery system parts formed of aluminum or an aluminum alloy,

said liquid fuel composition comprising N wt.% of an alcohol component of an aliphatic

monohydric alcohol having 2 to 6 carbon atoms per molecule or a mixture thereof, wherein N

is 2 to 85 wt.%, and 15 to 98 wt.% of a hydrocarbon component,

said liquid fuel composition containing an effective amount of water for inhibiting dry

corrosion of the aluminum and aluminum alloy parts when said parts are exposed to a

temperature in the range of 80°C to 120°C, wherein said liquid fuel composition contains water

at an amount equal to either (1) 0.002 \times N wt.% or more or (2) 0.1 wt.% or more of the

resulting liquid fuel composition, provided that the larger amount of admixed water is selected

between said (1) $0.002 \times N$ wt.% or more and said (2) 0.1 wt.% or more of the resulting liquid

fuel composition.

Claim 12 (new): A liquid fuel composition for an internal combustion engine having fuel

delivery system parts formed of aluminum or an aluminum alloy,

HAYES SOLOWAY P.C. 3450 E. SUNRISE DRIVE, SUITE 140 TUCSON, AZ 85718 TEL. 520.882.7623 FAX. 520.882,7643

175 CANAL STREET MANCHESTER, NH 03101 TEL. 603.668.1400 FAX. 603.668.8567

2

said liquid fuel composition comprising 2 to 85 wt.% of an alcohol component of an aliphatic monohydric alcohol having 2 to 6 carbon atoms per molecule or a mixture thereof, and 15 to 98 wt.% of a hydrocarbon component,

said liquid fuel containing an effective amount of a aluminum dry corrosion inhibitor for inhibiting dry corrosion of the aluminum and aluminum alloy parts when said parts are exposed to a temperature in the range of 80°C to 120°C, wherein said aluminum dry corrosion inhibitor is at least one compound selected from the group consisting of a glycol hydrocarbon, a ketone hydrocarbon, an ester hydrocarbon and an aldehyde hydrocarbon.

Claim 13 (new): The liquid fuel composition according to claim 12 wherein said glycol hydrocarbon is selected from the group consisting of ethylene glycol and propylene glycol; said ketone hydrocarbon is selected from the group consisting of acetone, dimethyl ketone, methyl ethyl ketone, diethyl ketone, methyl-n-propyl ketone, methyl isobutyl ketone, and acetyl acetone; said ester hydrocarbon is selected from the group consisting of methyl formate, ethyl formate, methyl acetate, and ethyl acetate; and said aldehyde hydrocarbon is selected from the group consisting of acetoaldehyde, propionaldehyde, and butylaldehyde.

Claim 14 (new): The liquid fuel composition according to claim 12, further including at least an additional aluminum dry corrosion inhibitor wherein said additional aluminum dry corrosion inhibitor is water.

Claim 15 (new): The liquid fuel composition according to claim 12, further including at least one kind of ether components having not more than 12 carbon atoms per molecule.

Claim 6 (new): The liquid fuel composition according to claim 14, further including at least one kind of ether components having not more than 12 carbon atoms per molecule.

HAYES SOLOWAY P.C. 3450 E. SUNRISE DRIVE, SUITE 140 TUCSON, AZ 85718 TEL. 520.882.7623 FAX. 520.882.7643

Claim 17 (new): A method for preventing dry corrosion of aluminum or aluminum alloy parts of a fuel delivery system of an internal combustion engine, wherein the fuel is a synthetic liquid fuel containing an alcohol, and the parts are exposed to a temperature in the range of 80°C to 120°C,

said method comprising adding to the liquid fuel an effective amount of water to prevent dry corrosion of the aluminum or aluminum alloy parts wherein said liquid fuel comprises N wt.% of an aliphatic monohydric alcohol component having 2 to 6 carbon atoms per molecule or a mixture thereof, wherein N is 2 to 85 wt.%, and 15 to 98 wt.% of a hydrocarbon component, in admixture with water at an amount equal to either (1) $0.002 \times N$ wt.% or more or (2) 0.1 wt.% or more of the resulting liquid fuel composition, provided that the larger amount of admixed water is selected between said (1) $0.002 \times N$ wt.% or more and said (2) 0.1 wt.% or more of the resulting liquid fuel composition.

Claim 18 (new): A method for preventing dry corrosion of aluminum or aluminum alloy parts of a fuel delivery system of an internal combustion engine, wherein the fuel is a synthetic liquid fuel containing an alcohol, and the parts are exposed to a temperature in the range of 80°C to 120°C,

said method comprising adding to said liquid fuel an effective amount of a corrosion inhibitor for inhibiting dry corrosion of said aluminum or aluminum alloy parts wherein said aluminum dry corrosion inhibitor is at least one compound selected from the group consisting of a glycol hydrocarbon, a ketone hydrocarbon, an ester hydrocarbon and an aldehyde hydrocarbon, wherein said liquid fuel comprises 2 to 85 wt.% of an aliphatic monohydric

HAYES SOLOWAY P.C. 3450 E. SUNRISE DRIVE, SUITE 140 TUCSON, AZ 85718 TEL. 520.882.7623 FAX. 520.882.7643

alcohol component having 2 to 6 carbon atoms per molecule or a mixture thereof, and 15 to 98 wt.% of a hydrocarbon component.

Claim 19 (new): The method according to claim 18, wherein said glycol hydrocarbon is selected from the group consisting of ethylene glycol and propylene glycol; said ketone hydrocarbon is selected from the group consisting of acetone, dimethyl ketone, methyl ethyl ketone, diethyl ketone, methyl-n-propyl ketone, methyl isobutyl ketone, and acetyl acetone; said ester hydrocarbon is selected from the group consisting of methyl formate, ethyl formate, methyl acetate, and ethyl acetate; and said aldehyde hydrocarbon is selected from the group consisting of acetoaldehyde, propionaldehyde, and butylaldehyde.

Claim 20 (new): The method according to claim 18, wherein said liquid fuel composition further includes at least an additional aluminum dry corrosion inhibitor wherein said additional aluminum dry corrosion inhibitor is water.

Claim 21 (new): The method according to claim 18, wherein said liquid fuel composition further includes at least one kind of ether components having not more than 12 carbon atoms per molecule.

Claim 22 (new): The method according to claim 20, wherein said liquid fuel composition further includes at least one kind of ether components having not more than 12 carbon atoms per molecule.

Claim 23 (new): A method for preventing dry corrosion of aluminum or aluminum alloy parts of a fuel delivery system of an internal combustion engine wherein the fuel is a synthetic liquid fuel containing an alcohol, and the parts are exposed to a temperature in the range of 80°C to 120°C,

HAYES SOLOWAY P.C. 3450 E. SUNRISE DRIVE, SUITE 140 TUCSON, AZ 85718 TEL. 520.882.7623 FAX. 520.882.7643

said method comprising adding to the liquid fuel an effective amount of water to prevent dry corrosion of the aluminum or aluminum alloy parts wherein said liquid fuel comprises N wt.% of an aliphatic monohydric alcohol component having 2 to 6 carbon atoms per molecule or a mixture thereof, wherein N is 2 to 85 wt.%, 15 to 98 wt.% of a hydrocarbon component and at least one kind of ether components having not more than 12 carbon atoms per molecule, in admixture with water at an amount equal to either (1) $0.002 \times N$ wt.% or more or (2) 0.1 wt.% or more of the resulting liquid fuel composition, provided that the larger amount of admixed water is selected between said (1) $0.002 \times N$ wt.% or more and said (2) 0.1 wt.% or more of the resulting liquid fuel composition.

HAYES SOLOWAY P.C. 3450 E. SUNRISE DRIVE, SUITE 140 TUCSON, AZ 85718 TEL. 520.892.7623 FAX. 520.892.7643